## MATERIAL SAFETY DATA SHEET

## ANTHRACITE GREY

Version Number 1.0 Revision Date 02/24/2005 Page 1 of 7 Print Date 11/17/2011

#### 1. PRODUCT AND COMPANY IDENTIFICATION

#### POLYONE CORPORATION 33587 Walker Road, Avon Lake, OH 44012

Telephone:Emergency telephone:number		Product Stewardship (440) 930-1395 CHEMTREC 1-800-424-9300 (24hrs for spill, leak, fire, exposure or accident).
Product name	:	ANTHRACITE GREY
Product code	:	CC10065200
Chemical Name	:	Mixture
CAS-No.	:	Mixture
Product Use	:	Industrial Applications

#### 2. COMPOSITION/INFORMATION ON REGULATED INGREDIENTS

Components	CAS-No.	Weight %
Carbon black	1333-86-4	1 - 5
Titanium dioxide	13463-67-7	5 - 10

#### **3. HAZARDS IDENTIFICATION**

#### **EMERGENCY OVERVIEW**

This mixture has not been evaluated as a whole. Information provided on the health effects of this product is based on individual components. All ingredients are bound and potential for hazardous exposure as shipped is minimal. However, some vapors may be released upon heating and the end-user (fabricator) must take the necessary precautions (mechanical ventilation, respiratory protection, etc.) to protect employees from exposure.

#### POTENTIAL HEALTH EFFECTS

Routes of Exposure:	: Inhalation, Ingestion, Skin contact
Acute exposure	
Inhalation	: Particulates, like other inert materials can be mechanically irritating. If overheated or burnt, the polymer releases formaldehyde.
Ingestion	: May be harmful if swallowed.
Eyes	: Particulates, like other inert materials can be mechanically irritating.
Skin	: Experience shows no unusual dermatitis hazard from routine handling.
Chronic exposure	: Refer to Section 11 for Toxicological Information.
Medical Conditions Aggravated by Exposure:	: None known.



# MATERIAL SAFETY DATA SHEET ANTHRACITE GREY

Version Number 1.0 Revision Date 02/24/2005 Page 2 of 7 Print Date 11/17/2011

	4. FIRST AID MEASURES
Inhalation	: Move to fresh air in case of accidental inhalation of fumes from overheating or combustion. When symptoms persist or in all cases of doubt seek medical advice.
Ingestion	: Do not induce vomiting without medical advice. When symptoms persist or in all cases of doubt seek medical advice.
Eyes	: Rinse immediately with plenty of water, also under the eyelids, for at least 15 minutes. If eye irritation persists, seek medical attention.
Skin	: Wash off with soap and plenty of water. If skin irritation persists seel medical attention.
	5. FIRE-FIGHTING MEASURES
Flash point	: Not applicable
Flammable Limits Upper explosion limit Lower explosion limit Autoignition temperature Suitable extinguishing media Special Fire Fighting Procedures Unusual Fire/Explosion Hazards	<ul> <li>Not applicable</li> <li>Not applicable</li> <li>Not applicable</li> <li>Carbon dioxide blanket, water spray, dry powder, foamnone.</li> <li>Fullface self-contained breathing apparatus (SCBA) used in positive pressure mode should be worn to prevent inhalation of airborne contaminants.</li> <li>Carbon dioxide (CO2), carbon monoxide (CO), oxides of nitrogen (NOx), other hazardous materials, and smoke are all possible. If overheated or burnt, the polymer releases formaldehyde. May burn with invisible flame.</li> </ul>
Personal precautions	: Wear appropriate personal protection during cleanup, such as impervious gloves, boots and coveralls.
Environmental precautions	: Should not be released into the environment. The product should not be allowed to enter drains, water courses or the soil.
Methods for cleaning up	: Clean up promptly by sweeping or vacuum. Package all material in plastic, cardboard or metal containers for disposal. Refer to Section 12 of this MSDS for proper disposal methods.
	7. HANDLING AND STORAGE
Handling	: Take measures to prevent the build up of electrostatic charge. Open container only in a well-ventilated area. Heat only in areas with

PolyOne.

# MATERIAL SAFETY DATA SHEET ANTHRACITE GREY

Version Number 1.0 Revision Date 02/24/2005 Page 3 of 7 Print Date 11/17/2011

	:	appropriate exhaust ventilation. Keep containers dry and tightly closed to avoid moisture absorption and contamination. Keep in a dry, cool place.	
8. EXPOSU	UK	E CONTROLS / PERSONAL PROTECTION	
Respiratory protection	:	No personal respiratory protective equipment normally required. When temperatures exceed 230°C (446°F) and ventilation is inadequate to maintain concentrations below exposure limits, use a positive air supplied respirator. Air purifying respirators may not provide adequate protection.	
Eye/Face Protection	:	Safety glasses with side-shields. Wear face-shield and protective suit for abnormal processing problems.	
Hand protection	:	Protective gloves.	
Skin and body protection	:	Long sleeved clothing.	
Additional Protective Measures	:	Safety shoes.	
General Hygiene Considerations	:	Handle in accordance with good industrial hygiene and safety practice. Wash hands before breaks and at the end of workday.	
Engineering measures	:	Heat only in areas with appropriate exhaust ventilation. Provide appropriate exhaust ventilation at machinery.	

Exposure limit(s)

Components	Value	Exposure time	Exposure type	List:
Carbon black	3.5 mg/m3	Time Weighted Average	Total dust. as carbon	ACGIH
		(TWA):	black	
	3.5 mg/m3	PEL:	Total dust. as carbon	OSHA Z1
			black	
Titanium dioxide	10 mg/m3	Time Weighted Average		ACGIH
		(TWA):		
	15 mg/m3	PEL:	Total dust.	OSHA Z1

#### 9. PHYSICAL AND CHEMICAL PROPERTIES

Form Appearance Color Odor Melting point/range Boiling Point: Water solubility Solid
Pellets, Slabs
GREY
formaldehyde
Not determined
Not applicable
Insoluble

Evaporation rate Specific Gravity: Bulk density Vapor pressure Vapour density pH Not applicable
Not determined
Not established
Not applicable
Not applicable
Not applicable

PolvOne

### MATERIAL SAFETY DATA SHEET ANTHRACITE GREY

Version Number 1.0 Revision Date 02/24/2005

\_

Page 4 of 7 Print Date 11/17/2011

	10. STABILITY AND REACTIVITY
Stability	: Stable.
Hazardous Polymerization	: Will not occur.
Conditions to avoid	: Maintain polymer temperature below 230°C (446°F). Avoid prolonged exposure at or above recommended processing temperature.
Incompatible Materials	: Incompatible with strong oxidizers and with strong acids and bases (decomposes to form formaldehyde). At melt temperatures, acetal resins are incompatible with halogenated polymers such as vinyl (PVC) and any elastomers containing any halogenated polymers. At processing conditions, these materials are mutually destructive and involve rapid degradation. Even small amounts of such contaminants can cause sudden and spontaneous formaldehyde gas formation. Workplace fume well above threshold levels are a likely result. Unsafe pressurization of equipment such as extruder or mold can also result. Thoroughly purge and mechanically clean processing equipment to avoid even trace quantities of halogenated materials from coming in contact with the acetal. Prevent contamination of virgin or rework resin.
Hazardous decomposition products	: Carbon dioxide (CO2), carbon monoxide (CO), oxides of nitrogen (NOx), other hazardous materials, and smoke are all possible. If overheated or burnt, the polymer releases formaldehyde. Decomposition of this material depends on the lenght of time it is exposed to elevated temperatures. At the recommended processing temperature of 210°C-220°C (410°F-428°F), decomposition should not be significant until after 30 minutes. Decomposition may be accelerated by contaminants, pigments and/or other additives.

**11. TOXICOLOGICAL INFORMATION** 

This mixture has not been evaluated as a whole for health effects. Exposure effects listed are based on existing health data for the individual components which comprise the mixture.

Toxicity Overview

This product contains the following components which in their pure form have the following characteristics:

CAS-No.	Chemical Name	Effect	Target Organ
1333-86-4	Carbon black	Systemic effects	Eyes, Respiratory system.
13463-67-7	Titanium dioxide	Systemic effects	Respiratory system.

LC50 / LD50

This product contains the following components which, in their pure form, have the following toxicity data:

CAS-No.	Chemical Name	Route	Value	Species



## MATERIAL SAFETY DATA SHEET

## ANTHRACITE GREY

Version Number 1.0 Revision Date 02/24/2005 Page 5 of 7 Print Date 11/17/2011

1333-86-4	Carbon black	Oral LD50	> 15,400  mg/kg	rat
		Dermal LD50	> 3 gm/kg	rabbit
Additional Health Haza Carbon black 1333-86 response observed in the exposure. However, the "There is sufficient evid this evaluation, along wi overall evaluation is tha listing only pertains to a been listed as a carcinog Health Administration ( criteria document on ca hydrocarbon) levels great	-4 Carcinogenicity: Me e referenced rat studie IARC evaluation in Mence in experimental a th their evaluation of t "Carbon Black is po irborne, unbound carl gen by the National To OSHA). The National rbon black recommen	s is species specific a lonograph Volume 6 unimals for the carcin inadequate evidence ssibly carcinogenic to bon black particles of xicology Program (N Institute of Occupat ds that only carbon b	nd does not correl 5, issued in April 1 nogenicity of carb of carcinogenicity o humans (Group f respirable size. C (TP) or the Occup ional Safety and H olack with PAH (p	ate to human 1996 concluded f on black". Based in humans, IAI 2B). The IARC Carbon Black ha ational Safety an Iealth (NIOSH)
	12. ECOLOG	ICAL INFORMATIO	ON	
Persistence and degradable	lity : Not readily	biodegradable.		
Environmental Toxicity	: Chemicals a polymer ma	re not readily availab	le as they are bound	l within the
Bioaccumulation Potentia	l : Chemicals a polymer ma	re not readily availab	le as they are bound	l within the
Additional advice	: Not applicat	ble		
	13. DISPOSA	L CONSIDERATIO	NS	
Product	possible rec generator of classificatio	nermoplastic plastics t ycling is preferred to waste material has th n, transportation and c ederal, state/provincia	disposal or incinera e responsibility for disposal in accorda	tion. The proper waste nce with
Contaminated packaging	has the resp	s preferred when possi onsibility for proper w l in accordance with a gulations.	vaste classification,	transportation
	14. TRANSPO	ORT INFORMATIC	N	
U.S. DOT Classification	-	ed for transportation.		
	: Refer to spe	cific regulation.		
ICAO/IATA (air)	·			

PolyOne.

Page 6 of 7 Print Date 11/17/2011

## POLYONE CORPORATION

## MATERIAL SAFETY DATA SHEET ANTHRACITE GREY

Version Number 1.0 Revision Date 02/24/2005

\_

		15. REGULATOR	Y INFORMATION		
US	Regulations:				
	OSHA Status	: Classified as haz	ardous based on com	ponents.	
	TSCA Status	: All components Inventory.	of this product are list	ed on or exemp	pt from the TS
US.	EPA CERCLA Hazardou	s Substances (40 CFR 3	302)		
	Not applicable				
	California Proposition	: This product doe	es not contain a substa	nce listed by C	alifornia Prop
	65				
	RA Title III Section 302 E Not applicable	xtremely Hazardous Sul	bstance		
SAF	RA Title III Section 313 T	oxic Chemicals:			
ן	Not applicable				
	adian Regulations:				
	National Pollutant Rele	ease Inventory (NPRI)			
-	Chemical Name		CAS-No.	Weight %	NPRI ID#
-	Phthalocyanine blue		147-14-8	0.18	71
		um huff			
-					
-	Phthalocyanine green Rutile, antimony chromin Rutile, antimony chromin		1328-53-6 68186-90-3 68186-90-3	0.18 0.42 0.24 0.24	71 71 69 17
	WHMIS Classification	n : D2A			
	WHMIS Ingredient Dis	sclosure List			
	CAS-No.				
	1333-86-4				
	1555-00-4				
	DSL		of this product are on (DSL) or are exempt.	the Canadian	Domestic
Nati	ional Inventories:				

PolyOne.

### MATERIAL SAFETY DATA SHEET ANTHRACITE GREY

Version Number 1.0 Revision Date 02/24/2005 Page 7 of 7 Print Date 11/17/2011

China IECS	: Listed
Europe EINECS	: Listed
Japan ENCS	: Not determined
Korea KECI	: Listed
Philippines PICCS	: Listed

#### **16. OTHER INFORMATION**

The information provided in this Safety Data Sheet is correct to the best of our knowledge, information and belief at the date of its publication. The information given is designed only as a guidance for safe handling, use, processing, storage, transportation, disposal and release and is not to be considered a warranty or quality specification. The information relates only to the specific material designated and may not be valid for such material when used in combination with any other materials and/or in any particular process or processing conditions.